



MICRO SYNTHETIC

Description

FORTA® NYLO-MONO® is an easy to finish micro synthetic fiber, made of 100% virgin nylon monofilament. This fiber is designed to function as a plastic shrinkage reinforcement intended to reduce the formation of shrinkage cracks prior to initial set and to reduce settlement shrinkage. NYLO-MONO is non-corrosive, chemically inert, and resistant to acid and alkali attack.

Reinforcement Objective

To inhibit concrete cracking caused by plastic and settlement shrinkage that occurs prior to the initial set.

Physical Properties

Specific Gravity	1.14
Density	1,938 lb/cu yd (1,150 kg/cu m)
Tensile Strength	140 ksi (966 MPa)
Length	0.75 in (19 mm)
Melting Point	509°F (265°C)
Material	Virgin Nylon
Form	Monofilament
Color	White
Acid / Alkali Resistance	Good
Absorption	Nil

Compliance & Certification

- ASTM C1116 / C1116M-10a, Standard Specification for Fiber-Reinforced Concrete
- ASTM D7508 / D7508M-10(2015), Standard Specification for Polyolefin Chopped Strands for Use in Concrete
- Certified UL / ULC: CBXQ.R18552
- DUNS: 094214129
- CAGE Code: OFAN8
- NAICS: 325220

Applications

NYLO-MONO is primarily used with cast-in-place concrete applications such as slabs-on-ground, overlays/toppings, curbs, driveways, sidewalks, basement floors, garage floors, and colored concrete – anywhere that the objective is to control plastic shrinkage cracking. Requires no mix design or placement changes!

Performance Benefits

- Increase surface durability
- Reduce plastic and settlement shrinkage
- Reduce settlement and bleeding
- Provide 3-dimensional reinforcement against micro-cracking

Recommended Dosage

This product is typically used at a minimum dosage rate of 1.0 lb/cu yd (0.6 kg/cu m) of concrete. Contact FORTA Corporation for design assistance and dosage recommendations.

Packaging

	Domestic	International
Bags	1.0 lb	0.6 kg
Cartons	50 bags	40 bags
Pallets	16 cartons/800 bags	12 cartons/480 bags

Recommendations

Addition: NYLO-MONO is packaged in mixer-ready bags that can be added directly into the concrete mixing system. The fiber should be added during or after batching of the other ingredients – never as the first mix ingredient.

Mixing: When possible, add fibers to a rotating drum. Once all fibers have been added to the batch, mix four to five minutes at standard mixing speed. Road-revolution speed should not be counted as part of the required fiber mixing time.

Slump: Fibers may reduce the visual slump measured by the slump-cone test, but has a lesser effect on flow-ability and workability. To regain any loss of workability or slump, the use of appropriate admixtures is recommended – avoid the addition of water.

Additional Information

Additional information such as the Safety Data Sheet, Certifications, videos and other literature can be found on the forta-ferro.com website. The website also features Project Profiles that show the many applications and benefits of FORTA products first-hand.

Warranty

FORTA® products are warranted to be free of defects in material and meet all quality control standards set by the manufacturer. FORTA Corporation specifically disclaims all other warranties, express or implied. The exclusive remedy for defective product shall be to replace the product or refund the purchase price. No agent or employee of this company is authorized to vary the terms of this warranty notice. FORTA Corporation has no control over the design, production, placement, or testing of the concrete products in which FORTA® products are incorporated, and therefore FORTA Corporation disclaims liability for the end product.

FORTA reserves the right to change the features and specifications of its products without prior notice.

NYLO-MONO® can be purchased from FORTA Corporation or an authorized FORTA® products distributor, dealer or representative.

FORTA®, NYLO-MONO®, and “Circles of Strength” mark are registered trademarks of FORTA Corporation

© 2018 FORTA Corporation

MADE IN



U. S. A.

FD.5.1.03.18