


## PC<sup>®</sup> CARBOCOMP TEXTILE 225

### 1. Description

Unidirectional carbon fibre textile with carbon fibres in the longitudinal direction. This textile is protected against pollution by a membrane.



### 2. Applications

Increase of the bearing capacity of columns from bridges, buildings.

Increase of the shear strength of beams.

For example in the following cases:

- Repair of the original bearing capacity, like after a fire or corrosion of the rebars.
- To increase the load bearing capacity of beams and columns.
- To repair errors during construction.

### 3. Advantages

- High tensile strength and stiffness
- Easy to apply
- Very little creep
- Flexible in use
- Excellent corrosion, acid and alkali resistance
- High durability
- Little thermal expansion
- Maintenance free, does not corrode



Terbekehofdreef 50-52  
B-2610 Wilrijk

phone +32 3 828.94.95  
fax +32 3 830.27.69

info@tradecc.be  
www.tradecc.be

#### 4. Technical properties

Properties	Technical Characteristics
Weight	225 g/m <sup>2</sup>
Roll width	± 300 mm
Roll length	150 m
Fabric equivalent thickness	0,125 mm
Fabric cross area per unit width	125 mm <sup>2</sup> /m
Tensile strength	4000 MPa
Stiffness	240 GPa
Max. elongation	1,60%
Density	1,80 g/cm <sup>3</sup>
Water absorption	< 0,1 percent by weight
Application temperature	- 40°C till +130°C

The above values are typical and indicative only. The achievable properties obtained from tensile test are dependant on the impregnating/laminating resin used and the type of tensile testing procedure. Apply material reduction factors according to the relevant design standard.

#### 5. Application

Apply the PC<sup>®</sup> 5800 resin on the element to be reinforced. Press the **PC<sup>®</sup> CarboComp Textile** into the wet resin. Please ventilate with a profiled roll. Then immediately apply a layer of PC<sup>®</sup> 5800 Carbo on the carbon fibre textile. The consumption of PC<sup>®</sup> 5800 Carbo varies in function of the roughness and porosity of the surface (estimated consumption: 500 g/m<sup>2</sup>).