

Technical Commercial data Sheet

BITUVER **XB-5**

Waterproofing bitumen polymer membrane

BITUVER XB-5 membranes are realized with plastomeric (BPP) compound that reaches -5°C cold flexibility. The product has a good mechanical resistance and high dimensional stability. **BITUVER XB-5** is also available in the "TEX" version with "DECOTEX" treatment, consisting in the application on the upper face of a special black polypropylene tissue. **Bituver XB-5 MINERAL** è is available with natural or colored slates.

Application

- Use Personal Protective Equipment as requested by law;
- Clean properly the surface on which membranes has to be applied;
- The treatment of the application surface with Bituver ECOPRIVER water based bituminous primer is suggested;
- **BITUVER XB-5** is meant to be applied by flame with a gas propane blow torch by heating the lower face, covered with a special termofusibile film;
- Apply between $+5^{\circ}\text{C}$ and $+35^{\circ}\text{C}$.

Suggested uses

BITUVER XB-5 membranes can be used on all type of structures as base layers, intermediate layers, earth retention and foundation. **BITUVER XB-5 MINERAL** can be used also as top layers or under tiles. **BITUVER XB-5** (when painted) could be used as top layer.

Storage

It is advisable to keep the rolls in warehouse, not exposed to the sun rays and at a higher temperature than $+5^{\circ}\text{C}$. Keep the rolls in the upright position. If possible, avoid stacking pallets, especially with slated membranes. It is advisable to use the product within 2/3 months from delivery.



TYPE	REINFORCEMENT	UPPER FACING	THICKNESS WEIGHT/m2	m ² PER PALLET
Bituver XB-5 3 MM P	Polyester	Sand	3 mm	250
Bituver XB-5 4 MM P	Polyester	Sand	4 mm	230
Bituver XB-5 TEX 4 MM P	Polyester	Polypropylene TNT	4 mm	230
Bituver XB-5 MINERAL 4 KG P	Polyester	Slate	4 kg	250
Bituver XB-5 MINERAL 4,5 KG P	Polyester	Slate	4,5 kg	230

Dimensional features	Length	10 m - 1% (UNI EN 1848-1)	Toll. \geq
	Width	1 m - 1% (UNI EN 1848-1)	Toll. \geq
	Thickness	(UNI EN 1849-1)	Toll. 0,4 mm
	Weight/m2	(UNI EN 1849-1)	Toll. 10%



ISOVER SAINT-GOBAIN
è socio ordinario
del GBC ITALIA

CODICE: STCB 413
REVISIONE: 01
DATA: october 2017
PAGINA: Pag. 1 di 2

Saint-Gobain PPC Italia S.p.A. – Attività Isover
Sede: Via Ettore Romagnoli, 6 – 20146 Milano

Servizio Clienti Bituver: Via G.Pastore, 15 - 66013 Chieti Scalo (CH) - Tel. 0871/588021 - Fax 0871/ 552483
www.bituver.it



BITUVER **XB-5**

Test	Rif. Norma	BITUVER XB-5 P	BITUVER XB-5 MINERAL P	TOLERANCES
Visible Faults	UNI EN 1850-1	assenti	assenti	-
Straightness	UNI EN 1848-1	10 mm	10 mm	≤
Water tightness	UNI EN 1928	60 kPa	60 kPa	≥
Cold flexibility	UNI EN 1109	- 5 °C	- 5 °C	≤
L dimensional stability	UNI EN 1107-1	- 0,3 %	- 0,3 %	≥
Flow resistance	EN 1110	120 °C	120 °C	≥
Flow resistance after ageing	UNI EN 1296 UNI EN 1110	110 °C	110 °C	- 10 °C
Tensile strength at breaking L/T	UNI EN 12311-1	400/250 N/50 mm	400/250 N/50 mm	- 20 %
Elongation at breaking L/T	UNI EN 12311-1	35/35 %	35/35 %	- 15 v.a
Tear resistance (B method) L/T	UNI EN 12310-1	130/130 N	130/130 N	- 30 %
Static load resistance	UNI EN 12730	10 Kg	10 Kg	≥
Dynamic punching resistance	UNI EN 12691	700 mm	700 mm	≥
Vapour permeability	UNI EN 1931	μ 20000	μ 20000	-
UV ageing	UNI EN 1297	Pass the test (4 mm)	-	-
Fire reaction	EN 13501-1	NPD	NPD	-
External fire reaction	EN 13501-5	F roof	F roof	-
Granules adhesion	UNI EN 12039	-	30%	≤
Water tightness after exposure to chemical agents artificial ageing	UNI EN 1928 UNI EN 1847/ UNI EN 1296	NPD	-	-
Resistance to water penetration	UNI EN 1928	-	CLASSE W1	-
Res. to water penetration Tensile properties after artificial ageing	App. C EN 13859-1	-	NPD	-
Uses	EN 13707 Sistema 2+	Base layer Middle layer Top layer (*)	Top layer	-
	EN 13969 Sistema 2+	Foundation Earth retention	-	-
	EN 13859-1 Sistema 4	-	Under tiles	-

(*) 4mm with protective paint

The Saint-Gobain PPC Italia S.p.A. quality system is certified according to EN ISO 9001. Follow proper application and storage modalities. The CE marking of this bituminous membrane is in accordance with the European Construction Products Regulation 305/2011, is in agreement to the reference technical standards and is supported by certification no. 1370-CPR-0050. Saint Gobain PPC Italia has the right to change the technical data of this data sheet any time with no need of notice



Isover Saint-Gobain è socio ordinario del GBC Italia

CODICE: STCB 413
REVISIONE: 01
DATA: october 2017
PAGINA: Pag. 2 di 2



Saint-Gobain PPC Italia S.p.A. – Attività Isover

Sede: Via Ettore Romagnoli, 6 – 20146 Milano

Servizio Clienti Bituver: Via G.Pastore, 15 - 66013 Chieti Scalo (CH) - Tel. 0871/588021 - Fax 0871/ 552483

www.bituver.it