



FOAMGLAS® TAPERED F

Page: 1 Date: 15.04.2013 Supersedes: 01.02.11 www.foamglas.com



FOAMGLAS® TAPERED F consists of FOAMGLAS® F slabs which are tapered across their width, or sometimes their length. A central arrow stamped onto the top surface indicates the direction of fall.

Form of delivery


length x width [mm]	600 x 450						
average thickness [mm]	60	70	80	90	100	110	120
length x width [mm]	600 x 450						
average thickness [mm]	130	140	150	160			

Standard angles of inclination:
 1.1%, 1.3%, 1.7%, 2.0%, 2.8%, 3.0%, 3.3%, 4.0%, 4.4%, 5.0%, 5.6%, 6.7%.
 Other dimensions and thicknesses are available on request.

General FOAMGLAS® Cellular Glass Insulation characteristics

- Description : FOAMGLAS® Insulation is manufactured from specially graded recycled glass (≥ 60%) and natural raw materials which are available in abundant supply (sand, dolomite, lime...). The insulation is totally inorganic, contains no ozone depleting propellants, flame resistant additives or binders. Without VOC or other volatile substances.
- Reaction to fire (EN 13501-1) : Material complying with Euroclass A1, non-combustible, no toxic fumes
- Service temperature limits : from -265°C to +430°C
- Water vapour resistance (EN ISO 10456) : $\mu = \infty$
- Hygroscopicity : zero
- Capillarity : zero
- Melting point (cf DIN 4102-17) : >1000 C°
- Thermal expansion coefficient (EN 13471) : $9 \times 10^{-6} K^{-1}$
- Specific heat (EN ISO 10456) : 1000 J/(kg·K)

FOAMGLAS® characteristics





FOAMGLAS® TAPERED F

Page: 2

Date: 15.04.2013

Supersedes: 01.02.11

www.foamglas.com

1. Product characteristics according to EN 13167 ¹⁾

Density (± 10%) (EN 1602)	: 165 kg/m ³
Thickness, average (EN 823) ± 2 mm	: from 60 to 160 mm
Length (EN 822) ± 2 mm	: 600 mm
Width (EN 822) ± 2 mm	: 450 mm
Thermal conductivity (EN ISO 10456)	: $\lambda_D \leq 0,050$ W/(m·K)
Reaction to fire (EN 13501-1)	: Euroclass A1
Point load (EN 12430)	: PL $\leq 1,0$ mm
Compressive strength (EN 826 annexe A)	: CS ≥ 1600 kPa
Bending strength (EN 12089)	: BS ≥ 550 kPa
Tensile strength (EN 1607)	: TR ≥ 150 kPa

¹⁾ CE-marking ensures conformity with the mandatory essential requirements of CPD as mentioned in EN 13167; within the CEN Keymark certification all mentioned characteristics are certified by an empowered, notified and accredited 3rd party.

2. Additional product data

Thermal diffusivity at 0°C	: 3.5×10^{-7} m ² /sec
λ_D -value and mean t° range (EN ISO 13787)	: + 35 °C ≤ 0.054 W/(m·K)
Product Conformity BS EN 13167 : 2001	: Nr. CL 07020029
BRE Green Guide Rating	: B
Natureplus certificate	: 0406-1101-101-1
Green Spec® Listed	: yes

3. Applications

TAPERED ROOF SYSTEM, cut-to-falls insulation system for highest compressive strength requirements:

- flat roofs (f.i. trafficable decks)
- floors